

# Exceed™ S 9333 Series

## Performance Polymer

### Product Description

Exceed™ S 9333 resin is a performance linear low density polyethylene 1-hexene copolymer designed to deliver a combination of high stiffness, high toughness, and exceptionally easy extrusion for a range of blown and cast applications. Similar to other Exceed™ S polyethylene products, the resin is well-suited for stiff-tough functional layers. The higher melt index, lower melt pressure and lower melt temperature of Exceed™ S 9333 relative to the other Exceed™ S PE grades helps it run well on equipment that is sensitive to high melt pressure or temperature limitations. TnPP is not intentionally added to Exceed™ S 9333 resin.

### General

Availability <sup>1</sup>	<ul style="list-style-type: none"> <li>▪ Africa &amp; Middle East</li> <li>▪ Asia Pacific</li> </ul>	<ul style="list-style-type: none"> <li>▪ Europe</li> <li>▪ Latin America</li> </ul>	<ul style="list-style-type: none"> <li>▪ North America</li> </ul>
Additive	<ul style="list-style-type: none"> <li>▪ Exceed S 9333ML: Antiblock: No; Slip: No; Processing Aid: Yes; Thermal Stabilizer: Yes</li> <li>▪ Exceed S 9333MR: Antiblock: No; Slip: No; Processing Aid: No; Thermal Stabilizer: Yes</li> </ul>		
Applications	<ul style="list-style-type: none"> <li>▪ Blown Film</li> <li>▪ Cast Film</li> </ul>	<ul style="list-style-type: none"> <li>▪ Food &amp; Liquid Packaging</li> <li>▪ Laminated Full-PE Packaging</li> </ul>	<ul style="list-style-type: none"> <li>▪ Lamination Film</li> <li>▪ Non-Laminated Coex Film</li> </ul>
Revision Date	<ul style="list-style-type: none"> <li>▪ 12/06/2022</li> </ul>		

### Resin Properties

	Typical Value (English)	Typical Value (SI)	Test Based On
Density / Specific Gravity	0.925 g/cm <sup>3</sup>	0.925 g/cm <sup>3</sup>	ASTM D792
Melt Index (190°C/2.16 kg)	2.0 g/10 min	2.0 g/10 min	ASTM D1238
Peak Melting Temperature	255 °F	124 °C	ExxonMobil Method

### Film Properties

	Typical Value (English)	Typical Value (SI)	Test Based On
Tensile Strength at Yield MD	1700 psi	11 MPa	ASTM D882
Tensile Strength at Yield TD	1800 psi	13 MPa	ASTM D882
Tensile Strength at Break MD	9200 psi	60 MPa	ASTM D882
Tensile Strength at Break TD	7300 psi	50 MPa	ASTM D882
Elongation at Break MD	560 %	560 %	ASTM D882
Elongation at Break TD	690 %	690 %	ASTM D882
Secant Modulus MD - 1% Secant	38000 psi	260 MPa	ASTM D882
Secant Modulus TD - 1% Secant	48000 psi	330 MPa	ASTM D882
Dart Drop Impact	460 g	460 g	ASTM D1709A
Elmendorf Tear Strength MD	210 g	210 g	ASTM D1922
Elmendorf Tear Strength TD	480 g	480 g	ASTM D1922
Puncture Force	9 lbf	40 N	ExxonMobil Method
Puncture Energy	24 in-lb	2.7 J	ExxonMobil Method

### Optical Properties

	Typical Value (English)	Typical Value (SI)	Test Based On
Gloss (45°)	32	32	ASTM D2457
Haze	21 %	21 %	ASTM D1003

### Legal Statement

Contact your ExxonMobil Chemical Customer Service Representative for potential food contact application compliance (e.g. FDA, EU, HPFB).

This product is not intended for use in medical applications and should not be used in any such applications.

Tris(nonylphenol)phosphite (TNPP) CAS# 26523-78-4 is not intentionally used by ExxonMobil in this product. Although this product is not routinely tested for its presence, based on product composition knowledge this substance is not expected to be present. However, the fact that this substance is not intentionally used by ExxonMobil in this product does not exclude that trace levels of this substance may be present as a result of the specific characteristics of the raw materials and/or of the manufacturing process.

### Processing Statement

Film (1 mil / 25.4 micron) made from Exceed™ S 9333ML on a 3.5 inch (90 mm) blown film line with a 2.5:1 blow-up ratio, a target melt temperature of 400°F (204°C), a 60 mil (1.5 mm) die gap at a rate of 15 lbs/hr/in die circumference.

## Exceed™ S 9333 Series Performance Polymer

### Notes

Typical properties: these are not to be construed as specifications.

<sup>1</sup> Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

For additional technical, sales and order assistance: [www.exxonmobilchemical.com/ContactUs](http://www.exxonmobilchemical.com/ContactUs)

©2024 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Product Solutions" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Product Solutions Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.

[exxonmobilchemical.com](http://exxonmobilchemical.com)