

# LUTENE-H ME1000S

High Density Polyethylene

## Applications

- Cap & Closure for beverage bottles of sparkling water
- Hot-fill and Carbonated soft drinks

## Description

- LUTENE-H ME1000S is mainly intended for injection molding and compression molding of bottle caps and closures.
- It has an excellent environmental stress crack resistance and organoleptic property.
- With slip agent

## Typical properties

Characteristics	Test Method	Unit	Value
<b>Physical<sup>(1)</sup></b>			
Density	ASTM D792	g/cm <sup>3</sup>	0.952
MFR(190 °C, 2.16Kg)	ASTM D1238	g/10min	0.9
Softening Point (Vicat)	ASTM D1525	°C	123
<b>Mechanical<sup>(2)</sup></b>			
Tensile Strength at Yield point	ASTM D638 <sup>(3)</sup>	kg/cm <sup>2</sup>	260
Elongation at Break	ASTM D638 <sup>(3)</sup>	%	>700
Shore hardness(Shore D)	ASTM D2240	-	64
Flexural Modulus1% Secant	ASTM D790	kg/cm <sup>2</sup>	8,000
IZOD Impact Strength at 23 °C (notched)	ASTM D256	kg·cm/cm	8
<b>Thermal</b>			
Melting Temperature	LG	°C	131

(1) The properties data in this table are typical values, and not guaranteed specification.

(2) Typical resin property values are measured on a standard compression molded specimens

(3) Speed of 50 mm/min.

## Processing information

- LUTENE-H ME1000S may be processed on conventional equipment. It is recommended that the melt temperature be kept below 250°C as decomposition can occur at higher temperature.

For additional sales, order and technical assistance

Revised: 13/11/2019

**Head office** PO Division, LG Chem Ltd.  
Yeoui-do P.O.Box 672, 21<sup>st</sup> floor LG Twin Tower,  
Yeoui-daero 128, Yeongdeungpo-gu Seoul, Korea.  
Tel. 82-2-3773-7804

**TS&D**

**Tech Center**

211, Hwangsae-ro, Osan-si, Gyeonggi-do,  
18126, Korea.  
Tel. 82-31-5187-0210

The information contained herein, including, but not limited to, data, statements and typical values, are given in good faith. LG Chem makes no warranty or guarantee, expressed or implied, (i) that the result described herein will be obtained under end - use conditions, or (ii) as to the effectiveness or safety of any design incorporating LG Chem materials, products, recommendations or advice. Further, any information contained herein shall not be construed as a part of legally binding offer. Especially, the typical values should be regarded as reference values only and not as binding minimum values. Each user bear full responsibility for making its own determination as to the suitability of LG Chem's materials, products, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating LG Chem material or products will be safe and suitable for use under end - use conditions. The data contained herein can be changed without notice as a result of the quality improvement of the products."